

# ROKESTER 2430

<b>CHEMICAL NAME</b>	Polyester polyol
<b>TECHNICAL REQUIREMENTS</b>	<p>Appearance at 25°C ..... homogenous, colorless to straw liquid (visually)</p> <p>Hydroxyl value, mg KOH/g ..... 230 – 250 (PN-EN ISO 2554:2001)</p> <p>Acid value, mg KOH/g ..... 1.60 – 2.0 (PN-EN ISO 2114:2005, solvent: acetone)</p> <p>Water, % (m/m) ..... max. 0.15 (PN ISO 760:2001)</p> <p>Dynamic viscosity at 25°C, mPas ..... 8000 – 12000 (PN-EN ISO 3219:2000, cone No.4 rpm 80)</p>
<b>INFORMATIVE DATA*</b>	<p>Functionality .....2</p> <p>Density at 25°C, g/ml .....~1.23</p> <p>* These informative data are not technical requirements and cannot form the basis for any claims.</p>
<b>APPLICATION</b>	Aromatic polyester polyol dedicated for the production of polyurethane rigid foams by the continuous lamination method.