

ROKESTER DP 1500.01

CHEMICAL NAME	Polyester polyol
TECHNICAL REQUIREMENTS	Appearance at 25°Chomogenous, colourless to straw liquid (visually) Hydroxyl value, mg KOH/g145 – 155 (PN-EN ISO 2554:2001) Acid value, mg KOH/gmax. 1,50 (PN-EN ISO 2114:2005, solvent: acetone) Water, % (m/m)max. 0.10 (PN-ISO 760:2001) Dynamic viscosity at 25°C, mPas1500 – 2500 (PN-EN ISO 3219:2000, cone No 2, rpm 110)
GENERAL DATA*	Density at 25°C, g/ml ~1,23
	* These informative data are not technical requirements and cannot form the basis for any claims.
APPLICATION	Aromatic polyester polyol intended for the production of one component polyurethane foams (OCF).