

ROKOPOL iCan 2850

CHEMICAL NAME	Polyether polyol, polyoxyalkylene triol based on glycerol
CAS NUMBER	31694-55-0
TECHNICAL REQUIREMENTS	<p>Appearance at 25°CHomogeneous, clear liquid</p> <p>Hydroxyl value, mg KOH/g 225 – 250 (ASTM D4274-16, met. D)</p> <p>Acid value, mg KOH/g.....max. 0.10 (ASTM D7253-16, bromothymol blue)</p> <p>Water content, % (m/m).....max. 0.10 (ASTM D4672-18)</p> <p>Colour, Hazen units max. 50 (ASTM D1209-05(2019))</p> <p>Dynamic viscosity at 25°C, mPas*180 – 280 (ASTM D4878-15, met. A)</p>

* parameter determined on customer's request

INFORMATIVE DATA**	<p>Molecular mass.....~700</p> <p>Density at temp. 25°C, g/ml ~1.070</p> <p>Flash point, °C above 230</p> <p>Content of Na+ + K+, mg/lmax. 5</p>
---------------------------	--

Contains BHT free antioxidants

** This information data does not constitute technical requirements and cannot be the basis for complaints.

APPLICATION	For the production of one-component foams, rigid polyurethane foams and other polyurethane-based materials.
--------------------	---