

ROKOPOL MH2012

CHEMICAL NAME Dispersion of styrene acrylonitrile copolymer in oxyalkylated triol

TECHNICAL REQUIREMENTS

Appearance at 25°CWhite, opaque liquid

Hydroxyl value, mg KOH/g 27 – 30
(ASTM D4274-16, met. D)

Water content, % (m/m) max. 0.08
(ASTM D4672-18)

Acid value, mg KOH/g max. 0.1
(ASTM D7253-16, bromothymol blue)

Dynamic viscosity at 25°C, mPas 1500 – 2500
(ASTM D4878-15, met. A)

GENERAL DATA***

Density at temp. 25°C, g/ml~1.03

Flash point, °Cabove 200

Contains BHT free antioxidants

***These informative data are not technical requirements and cannot form the basis for any claims.

APPLICATION For production of High Resilience block and moulded polyurethane foams.