

# ROKESTER DP 3500.01

**CHEMICAL NAME** Polyester polyol

**TECHNICAL REQUIREMENTS**

Appearance at 25°C .....viscous liquid  
(visually)

Hydroxyl value, mg KOH/g .....330 – 370  
(PN-EN ISO 2554:2001)

Acid value, mg KOH/g .....2.00 – 3.00  
(PN-EN ISO 2114:2005, solvent: acetone)

Water, % (m/m) .....max. 0.15  
(PN ISO 760:2001)

Dynamic viscosity at 25°C, mPas ..... 600 – 1000  
(PN-EN ISO 3219:2000, cone No 2, rpm 230)

**GENERAL DATA\*** Density at 25°C, g/ml ..... ~1,23

\*This information data does not constitute technical requirements and cannot be the basis for complaints.

**APPLICATION** Aromatic polyester polyol designed for production mining adhesives.