



PAINTS AND COATINGS
PAINTS

INDOOR ECOLABEL PAINT



INDOOR ECOLABEL PAINT

INGREDIENT		CONCENTRATION [%]
1	Water	17,0
2	EXOdis PC540i	0,6
3	EXOdis PC185	0,2
4	Defoamer	0,2
5	Titanium white	14,0
6	Plastorit 0000	5,0
7	Calplex 2	10,0
8	Socal P-2	7,0
9	Talc M15	7,0
10	Dorkafill H	7,0
11	Water	1,3
12	Hydroxyethylcellulose (1% aqueous solution)	10,0
13	Synexil SAB 05	20,0
14	Polyether thickener	0,4
15	Biocide	0,1
16	Defoamer	0,2



Wet-scrub resistance class	EN 13300	II
Viscosity	Brookfield, S64, 20rpm	10200 mPa·s
Gloss at 85°	ISO 2813	2.7
Contrast ratio at spreading rate 8 m²/l	ISO 6504-3	99,3%
Spreading rate at contrast ratio 98.0%	ISO 6504-3	10 m²/l

Procedure:

1. Mix components 1–4.
 2. Add components 5–10 slowly, while agitating, and mix until a homogeneous liquid is obtained.
 3. Grind until the desired fineness is achieved.
4. Add components 11–16 to the pigment slurry and mix until a homogeneous liquid is obtained.



The information in the catalogue is believed to be accurate and to the best of our knowledge, but should be considered as introductory only. Detailed information about products is available in TDS and MSDS. Suggestions for product applications are based on our the best of our knowledge.

The responsibility for the use of products in conformity or otherwise with the suggested application and for determining product suitability for your own purposes rests with the user.

All copyright, trademark rights and other intellectual and industrial property rights and the resulting rights to use this publication and its contents have been transferred to PCC Rokita SA, PCC EXOL SA and other companies of the PCC Group or its licensors. All rights reserved.

Users/readers are not entitled to reproduce this publication in whole or in part, nor are they entitled to reproduce it (excluding reproduction for personal use) or to transfer it to third parties.

Permission to reproduce it for personal use does not apply in respect to data used in other publications, in electronic information systems, or in other media publications. PCC Rokita SA and PCC EXOL SA shall not be responsible for data published by users.

Please visit our capital group business platform to check full range of products for paints and coatings.

www.products.pcc.eu

PCC Group
Sienkiewicza 4
56-120 Brzeg Dolny
Poland

e-mail: products@pcc.eu

