

ROKESTER 2600

CHEMICAL NAME Polyester polyol

TECHNICAL REQUIREMENTS

Appearance at 25°C viscous liquid,
straw to olive
(visually)

Hydroxyl value, mg KOH/g 250 – 270
(PN-EN ISO 2554:2001)

Acid value, mg KOH/g max 1.0
(PN-EN ISO 2114:2005, solvent: acetone)

Water, % (m/m) max. 0.10
(PN-ISO 760:2001)

Dynamic viscosity at 25°C, mPas 2500 – 4500
(PN-EN ISO 3219:2000, cone No 4, rpm 180)

INFORMATIVE DATA*

Functionality 2

Density at 25°C, g/ml ~1.24

* These informative data are not technical requirements and cannot form the basis for any claims.

APPLICATION

An aromatic polyester polyol intended for the production of one component polyurethane foams.