

## Polymax® ED-P4

<b>CHEMICAL NAME</b>	Polyether Polyol
<b>INCI NAME</b>	-
<b>CAS NUMBER</b>	102-60-3
<b>FUNCTION</b>	Plating Additive
<b>TECHNICAL REQUIREMENTS</b>	Color (APHA) ..... 70 Maximum Tertiary Amine..... 99 Maximum Water, % ..... 0.1 Maximum
<b>GENERAL DATA</b>	Appearance @ 25°C ..... Clear Liquid Specific Gravity @ 25°C..... 1.04 Pounds Per Gallon ..... 8.66 Average Molecular Weight ..... 716 Aqueous Solubility ..... Soluble
<b>APPLICATION</b>	Polymax® ED-P4 is commonly used in the stabilization of electroless copper plating baths. Recommended use level: 0.25 and 1.0% by wt

Revision Date: 24.05.2016