

## ROKOPOL X30

**CHEMICAL NAME** Polyol-based aqueous solution

**TECHNICAL REQUIREMENTS**

Appearance at 25°C.....	homogeneous, clear liquid
Water content, % (m/m).....	29 – 31 (ASTM D4672-18)
Dynamic Viscosity at 25°C, mPas*.....	30 – 60 (ASTM D4878-15, met. A)
Colour, Hazen units.....	max. 50 (ASTM D1209-05(2019))

\* parameter determined on customer's request

**INFORMATIVE DATA\*\*\***

Hydroxyl value, mg KOH/g.....	1110 – 1140
Density at temp. 25°C, g/ml.....	~1,25
Flash point, °C.....	above 200
Appearance bellow 15°C.....	possible opalescence
Does not contain antioxidants.	

\*\*\* These informative data are not technical requirements and cannot form the basis for any claims.

**APPLICATION** Rokopol X30 is designed as a cross-linking additive for flexible polyurethane foams.