

## ROKANATE M PE 2601

<b>CHEMICAL NAME</b>	Prepolymer based on diphenylmethane diisocyanate (MDI)
<b>TECHNICAL REQUIREMENTS</b>	<p>NCO content, % (m/m).....25.4 – 26.4 (PN-EN ISO 14896:2010)</p> <p>Density at 25°C, g/ml .....1.19 – 1.21 (PN-EN ISO 3675:2004)</p> <p>Dynamic viscosity at 20°C, mPas .....450 – 650 (ASTM D4878-15, met. A)</p> <p>Dynamic viscosity at 25°C, mPas .....300 – 450 (ASTM D4878-15, met. A)</p> <p>Dynamic viscosity at 30°C, mPas .....200 – 300 (ASTM D4878-15, met. A)</p> <p>Appearance/ colour at 25°C.....clear liquid, from light amber to amber</p>
<b>APPLICATION</b>	ROKANATE M PE 2601 is a one-component adhesive polyurethane for the production of lightweight boards wood-based so-called LDF. Contains no solvents and other dangerous compounds affecting the conditio health of living organisms, i.e. formaldehyde.