

## ROKESTER 2416

<b>CHEMICAL NAME</b>	Polyester polyol
<b>TECHNICAL REQUIREMENTS</b>	Appearance at 25°C ..... homogenous, clear liquid colorless to straw (visually) Hydroxyl value, mg KOH/g ..... 225 – 245 (PN-EN ISO 2554:2001) Acid value, mg KOH/g ..... 1,90 – 2,30 (PN-EN ISO 2114:2005, solvent acetone) Water, % (m/m) ..... max. 0,15 (PN ISO 760:2001) Dynamic viscosity at 25°C, mPas ..... 2500 – 4500 (PN-EN ISO 3219:2000, cone No.4, rpm 150)
<b>INFORMATIVE DATA*</b>	Density at 25°C, g/ml ..... ~1.23  * These informative data are not technical requirements and cannot form the basis for any claims.
<b>APPLICATION</b>	Aromatic polyol polyester dedicated to use in PUR / PIR foams.