

ROKOPOL iCan 2823

CHEMICAL NAME	Polyether polyol
CAS NUMBER	25791-96-2
TECHNICAL REQUIREMENTS	Appearance at 25°CHomogeneous, clear liquid Hydroxyl value, mg KOH/g 73 – 83 (ASTM D4274-16, met. D) Acid value, mg KOH/g.....max. 0.10 (ASTM D7253-16, bromothymol blue) Water content, % (m/m).....max. 0.10 (ASTM D4672-18) Colour, Hazen units max. 50 (ASTM D1209-05(2011)) Dynamic viscosity at 25°C, mPas*250 – 600 (ASTM D4878-15, met. A)

* parameter determined on customer's request.

INFORMATIVE DATA**	Density at temp. 25°C, g/ml ~1.01 Flash point, °C above 200 Content of Na+ + K+, mg/lmax. 5
---------------------------	---

Contains BHT free antioxidants

** This information data does not constitute technical requirements and cannot be the basis for complaints.

APPLICATION	Polyether polyol designed for one-component foam production.
--------------------	--