

## ROFLEX T70

<b>CHEMICAL NAME</b>	tert-butylphenyl-phenyl phosphate (Reaction mass of p-t-butylphenyldiphenyl phosphate and bis(p-t-butylphenyl) phenyl phosphate and triphenyl phosphate)
<b>CAS NUMBER</b>	-
<b>FUNCTION</b>	Plasticizer
<b>TECHNICAL REQUIREMENTS</b>	Appearance at 20-25°C..... homogenous, clear liquid Acid value, mg KOH/g..... max. 0.1 Density at 25 °C, g/cm <sup>3</sup> ..... 1.16-1.19 Viscosity at 25 °C, mPa·s..... 65-90 Flash point, °C ..... min. 230
<b>GENERAL DATA</b>	Other solvents ..... methanol, ethanol, acetone Odour ..... faint, ester Molecular weight, g/mol ..... 326-494 Halogen free
<b>APPLICATION</b>	Mainly recommended in PVC formulations, as well as flame retardants in synthetic rubber industry.