

## EKOPRODUR 1331B2

<b>CHEMICAL NAME</b>	Polyurethane system
<b>TECHNICAL REQUIREMENTS</b>	Weight ratio of components POLY : ISO..... 100 : 159 Optimal components temperature: ..... 18 - 22°C Ambient temperature: .... 18 - 35°C Temperature of the metal plate: ..... 20 - 40°C Temperature of the press: ..... 30 – 50 °C
<b>GENERAL DATA</b>	Apparent core density: ..... $\geq 40 \text{ kg/m}^3$ PN-EN 1602:2013-07  Steel surface should be free from dust, oil and water
<b>APPLICATION</b>	EKOPRODUR 1331B2 is design to be used in production of sandwich panels in continuous production line with mineral wool, EPS, or PU.