

# ROKESTER 1711

<b>CHEMICAL NAME</b>	Polyester polyol
<b>TECHNICAL REQUIREMENTS</b>	<p>Appearance at 25°C.....viscous liquid (visually)</p> <p>Hydroxyl value, mg KOH/g .....185 – 195 (PN-EN ISO 2554:2001)</p> <p>Acid value, mg KOH/g ..... 1.00 – 1.50 (PN-EN ISO 2114:2005, solvent: acetone)</p> <p>Water, % (m/m) ..... max. 0.10 (PN-ISO 760:2001)</p> <p>Dynamic viscosity at 25°C, mPas ..... 2500 – 3500 (PN-EN ISO 3219:2000, cone No.4 rpm 220)</p>
<b>GENERAL DATA</b>	Density at 25°C, g/ml ..... ~1.23
<b>APPLICATION</b>	Aliphatic-aromatic polyester polyol intended for production of one-component polyurethane foams (OCF) and PIR foams.