

ROKOPOL GS484

CHEMICAL NAME	Polyether polyol based on glycerol and sucrose
CAS NUMBER	-
TECHNICAL REQUIREMENTS	Appearance at 25°Chomogeneous liquid, yellow to brown Hydroxyl value, mg KOH/g465 – 505 (ASTM D4274-16, met.D) Acid value, mg KOH/g max. 0.1 (ASTM D7253-16, bromothymol blue) Water content, % (m/m) max. 0.1 (ASTM D4672-18) Dynamic Viscosity at 25°C, mPas* 6500 – 10000 (ASTM D4878-15, met. A) * – parameter determined on customer's request
GENERAL DATA	Density at 25°C, g/mL,~1.10 Flash point, °C above 200 Contains BHT free antioxidants
APPLICATION	Rokopol GS484 is a general purpose polyol for rigid foam systems, i.g.: in the production of spray thermal insulation systems, sandwich panels, block foam.