

ROKOPOL iCan 2812

CHEMICAL NAME Polyether polyol

CAS NUMBER 25791-96-2

TECHNICAL REQUIREMENTS

Appearance at 25°C Homogeneous, clear liquid

Hydroxyl value, mg KOH/g 105 – 115
(ASTM D4274-16, met. D)

Acid value, mg KOH/g max. 0.10
(ASTM D7253-16, bromothymol blue)

Water content, % (m/m) max. 0.10
(ASTM D4672-18)

Colour, Hazen units max. 50
(ASTM D1209-05(2011))

Dynamic viscosity at 25°C, mPas* 200 – 550
(ASTM D4878-15, met. A)

* parameter determined on customer's request.

INFORMATIVE DATA**

Density at temp. 25°C, g/ml ~1.01

Flash point, °C above 200

Content of Na+ + K+, mg/l max. 5

Contains BHT free antioxidants

** This information data does not constitute technical requirements and cannot be the basis for complaints.

APPLICATION Polyether polyol designed for one-component foam production.