

## ROKOPOL vTec 8860

**CHEMICAL NAME** Polyether polyol

**CAS NUMBER** -

**TECHNICAL REQUIREMENTS**

Appearance at 25°C ..... liquid free from suspended matter

Hydroxyl value, mg KOH/g ..... 110 – 125  
(ASTM D4274-16, met. D)

Acid value, mg KOH/g ..... max. 0.3  
(ASTM D7253-16, bromothymol blue)

Water content, % (m/m) ..... max. 0.3  
(ASTM D4672-12)

Dynamic viscosity at 25°C, mPas\* ..... 400 – 600  
(ASTM D4878-15, met. A)

\* – parameter determined on customer's request

**GENERAL DATA**

Density at temp. 25°C, g/ml ..... ~1.07

Flash point, °C ..... above 200

Contains BHT free antioxidants.

**APPLICATION** Experimental polyol vTec 8860 is specially designed for the production of MDI viscoelastic foam.