

ROKOPOL MOS 460

CHEMICAL NAME Stearyl alcohol, butoxylated

TECHNICAL REQUIREMENTS

Appearance at 25°C	homogeneous liquid, colourless to yellow
Water content, % (m/m)	max. 0.10 (ASTM D4672-24)
Hazen colour.....	max. 80 (ASTM D-1209-05 (2019))
Dynamic viscosity at 25°C, mPa-s.....	800 – 1400 (ASTM D4878-23, met. A)

GENERAL DATA**

Density at temp. 20°C, g/ml	~0.96
Hydroxyl number, mg KOH/g	13 – 30
Acid value, mg KOH/g	max. 0.10

**These informative data are not technical requirements and cannot form the basis for any claims.

APPLICATION Rokopol MOS 460 is used as an additive for polyurethane materials.