

ROKANATE M PE 2401

CHEMICAL NAME Prepolymer base on diphenylmethane diisocyanate (MDI).

TECHNICAL REQUIREMENTS

NCO content, % (m/m).....	24.0 – 25.0 (PN-EN ISO 14896:2010)
Density at 25°C, g/ml.....	1.16 – 1.18 (PN-EN ISO 3675:2004)
Dynamic viscosity at 25°C, mPas.....	200 – 500 (ASTM D4878-15, met.A)

APPLICATION Rokanate M PE 2401 is an isocyanate component, used for production of integral polyurethane foam. It can be processed on both low- and high pressure machines.