

ROKOPOL vTec8008

CHEMICAL NAME Polyether polyol

CAS NUMBER -

TECHNICAL REQUIREMENTS

Appearance at 25°CLiquid free from suspended matter
Hydroxyl value, mg KOH/g190-215
(ASTM D4274-16, met. D)
Water content, % (m/m).....max. 0.2
(ASTM D4672-18)
Acid value, mg KOH/g.....max. 0.2
(ASTM D7253-16, bromothymol blue)
Dynamic viscosity at 25°C, mPas*200-400
(ASTM D4878-15, met.A)

* parameter determined on customer's request

GENERAL DATA

Density at temp. 25°C, g/ml ~1.22
Flash point, °Cabove 200
Contains BHT free antioxidants

APPLICATION

Rokopol vTec8008 is specially dedicated to the production of viscoelastic foams based on T80/20 isocyanate. It can be combined with Rokopol M1170 to adjust cell openness and recovery time.