

## ROKANATE M PE 1701

**CHEMICAL NAME**                      Prepolymer based on diphenylmethane diisocyanate (MDI)

**TECHNICAL REQUIREMENTS**

NCO content, % (m/m) .....	17,0 – 18,5 (PN-EN ISO 14896:2010)
Density at 25°C, g/ml.....	1,14 – 1,17 (PN-EN ISO 2811-1:2023-03)
Dynamic viscosity at 25°C, mPas .....	150 – 300 (ASTM D4878-23, met. A)
Appearance at 25°C.....	liquid, colorless to yellow

**APPLICATION**                      Rokanate M PE 1701 is a one-component polyurethane adhesive used in the polyurethane industry e.g. for CASE.