

ROKESTER 1711

CHEMICAL NAME	Polyester polyol
TECHNICAL REQUIREMENTS	Appearance at 25°C homogenous, colorless to straw liquid (visually) Hydroxyl value, mg KOH/g 185 – 195 (PN-EN ISO 2554:2001) Acid value, mg KOH/g 1.00 – 1.50 (PN-EN ISO 2114:2005, solvent: acetone) Water, % (m/m) max. 0.10 (PN-ISO 760:2001) Dynamic viscosity at 25°C, mPas 2500 – 3500 (PN-EN ISO 3219:2000, cone No.4 rpm 220)
GENERAL DATA	Density at 25°C, g/ml ~1.23
APPLICATION	Aliphatic-aromatic polyester polyol intended for production of one-component polyurethane foams (OCF) and PIR foams.