

ROKANATE M PE 1501

CHEMICAL NAME	Prepolymer base on diphenylmethane diisocyanate (MDI)
TECHNICAL REQUIREMENTS	<p>NCO content, % (m/m).....15.0 – 16.0 (PN-EN ISO 14896:2010)</p> <p>Density at 25°C, g/ml1.10 – 1.13 (PN-EN ISO 3675:2004)</p> <p>Dynamic viscosity at 25°C, mPas700 – 1500 (ASTM D4878-15, met. A)</p> <p>Appearance/ colour at 25°C.....clear liquid, from light yellow to yellow</p>
APPLICATION	<p>ROKANATE M PE 1501 is an isocyanate component used in the production of spray polyurea coating.</p> <p>ROKANATE M PE 1501 has good joint stiffness while maintaining flexibility.</p>