

ROKESTER DP 1970.01

CHEMICAL NAME Polyester polyol

TECHNICAL REQUIREMENTS

Appearance at 25°C..... viscous liquid
(visually)

Hydroxyl value, mg KOH/g..... 180 – 200
(PN-EN ISO 2554:2001)

Acid value, mg KOH/g.....max. 1,00
(PN-EN ISO 2114:2005, solvent: acetone)

Water, % (m/m).....max. 0,10
(PN-ISO 760:2001)

Dynamic viscosity at 25°C, mPas 3000 – 8000
(PN-EN ISO 3219:2000, cone No.4, rpm 160)

INFORMATIVE DATA* Density at 25°C, g/ml ~1.23

* These informative data are not technical requirements and cannot form the basis for any claims.

APPLICATION Aromatic polyester polyol designed for production of PUR / PIR foams.