

## ROKESTER DP NV 2402.02

<b>CHEMICAL NAME</b>	Polyester polyol
<b>TECHNICAL REQUIREMENTS</b>	Appearance at 25°C.....homogenous liquid colorless to olive (visually) Hydroxyl value, mg KOH/g.....230 – 250 (PN-EN ISO 2554:2001) Acid value, mg KOH/g.....0.60 – 1.0 (PN-EN ISO 2114:2005, solvent: acetone) Water, % (m/m).....max. 0.15 (PN-ISO 760:2001) Dynamic viscosity at 25°C, mPas .....max 5 000 (PN-EN ISO 3219:2000, cone No.4, rpm 160)
<b>INFORMATIVE DATA*</b>	Density at 25°C, g/ml ..... ~1.23  * These informative data are not technical requirements and cannot form the basis for any claims.
<b>APPLICATION</b>	Specialized polyester polyol intended for applications in PUR/PIR foams..