

ROKOPOL iCan 2432

CHEMICAL NAME Polyether polyol

CAS NUMBER 9082-00-2

TECHNICAL REQUIREMENTS

Appearance at 25°C	Homogeneous clear liquid
Hydroxyl value, mg KOH/g.....	145 – 160 (ASTM D4274-16, met. D)
Acid value, mg KOH/g	max. 0.10 (ASTM D7253-16, bromothymol blue)
Water content, % (m/m).....	max. 0.10 (ASTM D4672-18)
Colour, Hazen units	max. 50 (ASTM D1209-05(2019))
Dynamic viscosity at 25°C, mPas*	150 – 250 (ASTM D4878-15, met. A)

* parameter determined on customer's request

GENERAL DATA

Density at temp. 25°C, g/ml	~1.020
Flash point, °C	above 200
Content of Na+ + K+, mg/l	max. 5
<u>Contains BHT free antioxidants</u>	

APPLICATION Special designed polyol intended for the production of onecomponent foams (OCF).