

SyncoPol S660

CHEMICAL NAME	Polyether polyol
TECHNICAL REQUIREMENTS	Appearanceclear liquid
	Hydroxyl value, mg KOH/g53 - 59
	Water content, % (m/m)max. 0.10
	Acid number, mg KOH/g 0.01 – 0.50
	Viscosity at 25°C, cps 26,000 – 40,000
APPLICATION	Multifunctional polyether polyol recommended for the production of rigid urethane foam. It is suitable for both high and low density foams. SyncoPol S660 can be used alone, or in combination with other polyols and fire retardants, to achieve various degrees of crosslinking.