

ROKANATE M PE 1503.60

CHEMICAL NAME	Prepolymer based on diphenylmethane diisocyanate (MDI).
TECHNICAL REQUIREMENTS	NCO content, % (m/m).....14.5 – 16.5 (PN-EN ISO 14896:2010) Density at 25°C, g/ml1.12 – 1.16 (PN-EN ISO 3675:2004) Dynamic viscosity at 25°C, mPas1500 – 3000 (ASTM D4878-15, met. A) Appearance/ colour at 25°C.....clear, dark amber liquid

INFORMATION DATA*** Open time, min*.....**60(+/-) 10**

* Fixed with a mist of water from an atomizer.

** It is possible to set other open times, according to the customer's needs.

***This information data does not constitute technical requirements and cannot be the basis for complaints.

APPLICATION Rokanate M PE 1503.60 is a one component polyurethane adhesive contains no organic solvents and have good flexibility of the joint. Ekoprodur RB-2 designed for gluing boards, among others fibrous, styrofoam, polyurethane, mineral wool with sheet, wood, gypsum boards, roofing paper. The adhesive retains its mechanical properties at a temperature of -40°C to + 80°C.