

## ROKOPOL M5020

<b>CHEMICAL NAME</b>	Polyether polyol, glycerine-based reactive polyoxyalkilenetriol
<b>CAS NUMBER</b>	9082-00-2
<b>TECHNICAL REQUIREMENTS</b>	Appearance at 25°C ..... Homogeneous clear liquid Hydroxyl value, mg KOH/g .....33 – 38 (ASTM D4274-16, met. D) Water content, % (m/m) .....max. 0.10 (ASTM D4672-12) Colour, Hazen units .....max. 50 (ASTM D1209-05(2011)) Acid value, mg KOH/g .....max. 0.10 (ASTM D7253-16, bromothymol blue) Dynamic viscosity at 25°C, mPas* .....700– 1000 (ASTM D4878-15, met.A) * parameter determined on customer's request
<b>GENERAL DATA</b>	Molecular weight ..... ~ 4850 Density at temp. 25°C, g/ml ..... ~1.020 Flash point, °C ..... above 200 Contains BHT free antioxidants
<b>APPLICATION</b>	For production of high resilience block and moulded polyurethane foams and other polyurethane plastics