

## ROKOPOL FS3615

<b>CHEMICAL NAME</b>	Dispersion of styrene acrylonitrile copolymer in oxyalkylated triol
<b>CAS NUMBER</b>	-
<b>TECHNICAL REQUIREMENTS</b>	Appearance at 25°C ..... White, opaque liquid Hydroxyl value, mg KOH/g ..... 37 – 43 (ASTM D4274-16, met. D) Water content, % (m/m)..... max. 0.08 (ASTM D4672-12) Acid value, mg KOH/g .....max. 0.1 (ASTM D7253-16, bromothymol blue) Dynamic viscosity at 25°C, mPas ..... 800 – 1200 (ASTM D4878-15, met. A) Solid content, % (m/m)* ..... ~ 15 (MB-0107)  * - parameter determined on customer's request
<b>GENERAL DATA</b>	Density at temp. 25°C, g/ml ..... ~1.025 Flash point, °C ..... above 200 <u>Contains BHT free antioxidants</u>
<b>APPLICATION</b>	For production of flexible polyurethane slabstock foams exhibiting increased load bearing characteristics.