

ROFLEX T70L

CHEMICAL NAME	Tert-butylphenyl-phenyl phosphate Reaction mass of p-t-butylphenyldiphenyl phosphate and bis(p-t-butylphenyl) phenyl phosphate
CAS No.	-
FUNKCJA	Plasticizer
TECHNICAL REQUIREMENTS	Appearance at 20-25 ° C homogeneous, clear liquid Acid value, mg KOH/g: max. 0.1 Density at 25°C g/cm ³ 1.10 - 1.15 Viscosity at. 25°C, mPa·s 200 - 400 Phenol content, % (m/m) max. 0.05 TPP contents, % (m/m) max. 2.5
GENERAL INFORMATION	Molecular weight, g/mol 400 - 450 Other solvents methanol, ethanol, acetone Odour is faint, typical for esters Halogen-free
ZASTOSOWANIE	Used as a softener in the processing of PVC and synthetic rubber.