

Rofluid T

CHEMICAL NAME	polycarboxylate ether solution
FUNCTION	Superplasticizer
TECHNICAL REQUIREMENTS	Appearance at 20-25°C light brown liquid pH 5.5-7.5 Dry matter, % (w/w) 49-51 Density at 20 °C, g/cm ³ 1.100-1.110
GENERAL DATA	Solubility in water good Viscosity [cP] 200-400 Odour weak, characteristic
APPLICATION	Used in a production of admixtures to concrete, especially precast concrete. It is fully compatible with other products of the Rofluid group.