

ROKESTER 3110

CHEMICAL NAME Polyester polyol

TECHNICAL REQUIREMENTS

Appearance at 25°Chomogenous, clear liquid
(visually)

Hydroxyl value, mg KOH/g300-330
(PN-EN ISO 2554:2001)

Acid value, mg KOH/gmax. 2-3
(PN-EN ISO 2114:2005, solvent: acetone)

Water, % (m/m)max. 0.15
(PN ISO 760:2001)

Dynamic viscosity at 25°C, mPas2000-3000
(PN-EN ISO 3219:2000, cone no.2, rpm 80)

INFORMATIVE DATA*

Functionality 2

Density at 25°C, g/ml ~1.24

* These informative data are not technical requirements and cannot form the basis for any claims.

APPLICATION

Rokester 3110 is an aromatic polyester polyol used in production of rigid polyurethane foams by laminating method.