Rokopol vTec8911

CHEMICAL NAME	Polyether polyol
CAS NUMBER	--
TECHNICAL REQUIREMENTS	Appearance at (25 °C)……...liquid free from suspended matter Hydroxyl value, mg KOH/g…135 – 150…ASTM D4274-11, test. D Water content, % (m/m)…… max. 0,3.….ASTM D4672-12 Acid value, mg KOH/g…….max. 0.2…..ASTM D7253-06(2011), bromothymol blue Viscosity at 25°C, mPas*…..450 – 650….ASTM D4878-08, test. A * – parameter determined on customer's request
GENERAL DATA	Density at temp. 25°C, g/ml..... ~1.08 Flash point, °C..... ……. above 200 Contains BHT free antioxidants.
APPLICATION	Specially designed for the production of MDI viscoelastic foam.

Information presented herein has been given in good faith and to the best of our current knowledge and experience.
The compliance of specific properties of the supplied product with the data given herein and its fitness for the intended purpose should be checked before the product is used. The producer reserves the right to modify the information presented herein as a result of technological development and improvement of the product by the producer.

PCC Rokita SA
ul. Sienkiewicza 4
56-120 Brzeg Dolny
Poland