

ROKESTER 1600.01

CHEMICAL NAME	Polyester polyol
TECHNICAL REQUIREMENTS	Appearance at 25°C homogenous, colorless to straw liquid (visually) Hydroxyl value, mg KOH/g 150 – 170 (PN-EN ISO 2554) Acid value, mg KOH/g max. 1.50 (PN-EN ISO 2114, solvent: acetone) Water, % (m/m) max. 0.15 (PN ISO 760, solvent: methanol+chloroform 1+3(V/V)) Dynamic viscosity at 25°C, mPas 1000 – 3000 (PN-EN ISO 3219, cone No.4, rpm 450)
GENERAL DATA	Density at 25°C, g/ml ~1.23
APPLICATION	Aromatic-aliphatic polyester polyol for application in PUR-PIR foams.