

## ROKOPOL V700

**CHEMICAL NAME** Polyether polyol, polyoxyalkylenetrol based on glycerol

**CAS NUMBER** 25791-96-2

**TECHNICAL REQUIREMENTS**

Appearance at 25°C .....	Homogeneous, clear liquid
Hydroxyl value, mg KOH/g.....	225 – 250 (ASTM D4274-16, met. D)
Water content, % (m/m).....	max. 0.10 (ASTM D4672-18)
Colour, Hazen units .....	max. 50 (ASTM D1209-05(2019))
Acid value, mg KOH/g.....	max. 0.1 (ASTM D7253-16, bromothymol blue)
Dynamic viscosity at 25°C, mPas* .....	220 – 270 (ASTM D4878-15, met.A)

\* parameter determined on customer's request

**GENERAL DATA**

Molecular weight .....	~700
Density at temp. 25°C, g/ml .....	~1.020
Flash point, °C .....	above 200
Contains BHT free antioxidants	

**APPLICATION** Used for the production of viscoelastic foam.