

ROKOPOL MS5215

CHEMICAL NAME Dispersion of styrene acrylonitrile copolymer in reactive oxyalkylated trio

CAS NUMBER -

TECHNICAL REQUIREMENTS

Appearance at 25°CWhite, opaque liquid

Hydroxyl value, mg KOH/g29 – 32
(ASTM D4274-16, met. D)

Water content, % (m/m) max. 0.08
(ASTM D4672-12)

Acid value, mg KOH/gmax. 0.1
(ASTM D7253-16 bromothymol blue)

Dynamic viscosity at 25°C, mPas 1200 – 1500
(ASTM D4878-15, met. A)

Solid content, % (m/m)*~ 15 (MB-0107)

* - parameter determined on customer's request

GENERAL DATA

Density at temp. 25°C, g/ml ~1.025

Flash point, °Cabove 200

Contains BHT free antioxidants

APPLICATION For production of High Resilience block and moulded polyurethane foams