

## ROKANATE M PE 0601

<b>CHEMICAL NAME</b>	Prepolymer based on diphenylmethane diisocyanate (MDI)
<b>TECHNICAL REQUIREMENTS</b>	<p>NCO content, % (m/m).....5.0 – 6.5 (PN-EN 1242:2013-06)</p> <p>Density at 25°C g/ml.....1.02 – 1.04 (PN-EN ISO 3675:2004)</p> <p>Dynamic viscosity at 25°C mPas.....450 – 900 (ASTM D4878-15, met. A)</p> <p>Appearance/ colour at 25°C.....clear liquid, from light yellow to amber</p>
<b>APPLICATION</b>	ROKANATE M PE 0601 is one component polyurethane adhesive used in the production of regenerated foam blocks (rebounding foam). ROKANATE M PE 0601 does not contain organic solvents. It is cured with moisture from blow-of water vapor.