ROKOPOL iCan 2672

CHEMICAL NAME	Polyether polyol, polyoxypropylenediol
CAS NUMBER	25322-69-4
TECHNICAL REQUIREMENTS	Appearance at 25°C .....Homogeneous, clear liquid Hydroxyl value, mg KOH/g .....150 – 170 (ASTM D4274-16, met. D) Acid value, mg KOH/g.....max. 0.10 (ASTM D7253-16, bromothymol blue) Water content, % (m/m).....max. 0.10 (ASTM D4672-18) Colour, Hazen units ..... max. 50 (ASTM D1209-05(2019) Dynamic viscosity at 25°C, mPas*.....50 – 150 (ASTM D4878-15, met. A) * parameter determined on customer's request.
INFORMATIVE DATA**	Density at temp. 25°C, g/ml .....~1.004 Flash point, °C ..... above 200 Content of Na+ + K+, mg/l .....max. 10 Contains BHT free antioxidants ** This information data does not constitute technical requirements and cannot be the basis for complaints.
APPLICATION	For the production of one-component foam (OCF), 1.5K and 2K foam, adhesives, elastomers, prepolymers and as one of main raw materials for aerosol coatings.

Information presented herein has been given in good faith and to the best of our current knowledge and experience. The compliance of the specific properties of the supplied product with the data given herein and its fitness for the intended purpose should be checked before the product is used. The producer reserved the right to modify the information presented herein as a result of technological development and improvement of the product by producer.

PCC Rokita SA
ul. Sienkiewicza 4
56-120 Brzeg Dolny
Polska
www.pcc.rokita.pl