

ROKOPOL RF170

CHEMICAL NAME	Polyether polyol, 2,2',2''-Nitrilotriethanol, propoxylated
CAS NUMBER	37208-53-0
TECHNICAL REQUIREMENTS	<p>Appearance at 25°C.....Amber liquid</p> <p>Hydroxyl value, mg KOH/g.....500 – 520 (ASTM D4274-16, test. D)</p> <p>Amine value, mg KOH/g.....165 – 175 MB – 0022</p> <p>Water content, % (m/m) max.....0.10 (ASTM D4672-18)</p> <p>Dynamic viscosity at 25°C, mPas*300 – 500 ASTM D4878-15, test. A</p> <p>* – parameter determined on customer's request</p>
GENERAL DATA	<p>Molecular weight.....330</p> <p>Density at temp. 25°C, g/ml.....~1.060</p> <p>pH 10% solution (Me:H2O).....max. 10.5</p> <p>Flash point, °Cabove 180</p> <p>Does not contain antioxidants</p>
APPLICATION	Rokopol RF170 is use as a component for production of rigid foam.