

Rokrysol JW20

CHEMICAL NAME	Mixture
TECHNICAL REQUIREMENTS	Appearanceyellow to brown, clear, viscous liquid Dry matter, % (m/m).....19 ÷ 21 pH of the product6.4 ÷ 7.0 Dynamic viscosity of 15% solution in terms of dry substance in 20°C , mPa·s.....1000 ÷ 2000
GENERAL DATA	Solidification point, °C approx. -5 Solubility in water unlimited Density in 20°C, g/ml.....1.05 ÷ 1.10
APPLICATION	Rokrysol JW20 is used in textile industry for producing washable adhesives.