

ROKESTER 3016

CHEMICAL NAME	Mixture of polyols
TECHNICAL REQUIREMENTS	<p>Appearance at 25°Chomogenous liquid (visually)</p> <p>Hydroxyl value, mg KOH/g270 – 300 (PN-EN ISO 2554:2001)</p> <p>Acid value, mg KOH/gmax. 2.30 (PN-EN ISO 2114:2005, solvent: acetone)</p> <p>Water, % (m/m)max. 0.15 (PN ISO 760:2001)</p> <p>Dynamic viscosity at 25°C, mPas2800 – 5300 (PN-EN ISO 3219:2000, cone No.4, rpm 180)</p>
INFORMATIVE DATA*	<p>Density at 25°C, g/ml ~1,20</p> <p>* These informative data are not technical requirements and cannot form the basis for any claims.</p>
APPLICATION	Branched, aromatic polyester polyol for specialist application.