

ROKOPOL GS364

CHEMICAL NAME	Polyether polyol based on glycerol and sucrose
CAS NUMBER	-
TECHNICAL REQUIREMENTS	<p>Appearance at 25°Chomogeneous liquid, yellow to brown</p> <p>Hydroxyl value, mg KOH/g..... 340 – 380 (ASTM D4274-11, test. D)</p> <p>Water content, % (m/m)..... max.0.10 (ASTM D4672-18)</p> <p>Acid value, mg KOH/g.....max 0.2 (ASTM D7253-16, bromothymol blue)</p> <p>Viscosity at 25°C, mPas*2 000 – 4 000 (ASTM D4878-15, test. A)</p> <p>* – parameter determined on customer's request</p>
GENERAL DATA	<p>Density at 25°C, g/mL.....~1.080</p> <p>Flash point, °C.....above 200</p> <p>Contains antioxidant BHT free.</p>
APPLICATION	Rokopol GS364 is a low viscosity poliol in general purpose rigid foam systems.