

ROFLEX R250

CHEMICAL NAME	Modified aryl phosphates
CAS NUMBER	-
FUNCTION	Plasticizer
TECHNICAL REQUIREMENTS	Appearance at 20-25°C..... homogenous, clear liquid Acid value, mg KOH/g..... max. 0.1 Density at 25 °C, g/cm ³ 1.25 - 1.27 Viscosity at 25 °C, mPa·s..... 209 - 290
GENERAL DATA	Other solvents methanol, ethanol, acetone Odour weak, ester Molecular weight, g/mol 326 - 574 Flash point, °C min. 225 Halogen free
APPLICATION	Used in the plastics industry as a plasticizer.