

SyncoPol AR 350

CHEMICAL NAME	Propoxylated Amine Base
CAS NUMBER	25214-63-5
FUNCTION	Reactive amine polyol for spray foam systems
TECHNICAL REQUIREMENTS	Apperance.....clear viscous liquid Color.....Colorless to pale yellow liquid Water Content, %.....max. 0,10 Hydroxyl Value, mg KOH/gm..... 620 - 660 Acid Number, mg KOH/gm..... 0,01 – 0,20 Total K+/Na+, ppmmax. 300
GENERAL DATA	Viscosity (25°C), cps16000 – 18000 Density (39°C), g/cm ³ 1,03 Odor..... odor
APPLICATION	Spray foam, panels and double band laminates for the construction industry and thermal insulation applications in the appliance and refrigeration industries.