

ROKOPOL MOS 68

CHEMICAL NAME Mixture of polyether polyols

TECHNICAL REQUIREMENTS

Appearance at 25°C	homogeneous liquid, colourless to yellow
Hydroxyl value, mg KOH/g.....	42 – 52 (ASTM D4274-23, met. D)
Acid value, mg KOH/g	max. 0.10 (ASTM D7253-22, bromothymol blue)
Water content, % (m/m).....	max. 0.10 (ASTM D4672-24)
Colour, Hazen units	max. 80 (ASTM D1209-05(2019))
Dynamic viscosity at 25°C, mPa·s	100 – 200 (ASTM D4878-23, met. A)

GENERAL DATA**

Density at temp. 20°C, g/ml	~0.95
Flash point, °C.....	above 240

Contains BHT free antioxidants

**These informative data are not technical requirements and cannot form the basis for any claims.

APPLICATION Rokopol MOS 68 is used as an additive for polyurethane materials.