

# ROKOPOL FS3640

<b>CHEMICAL NAME</b>	Dispersion of styrene acrylonitrile copolymer in oxyalkylated triol
<b>TECHNICAL REQUIREMENTS</b>	<p>Appearance at 25°C ..... White, opaque liquid</p> <p>Hydroxyl value, mg KOH/g ..... 25 – 30 (ASTM D4274-16, met. D)</p> <p>Water content, % (m/m) ..... max. 0.08 ASTM D4672-12)</p> <p>Acid value, mg KOH/g ..... max. 0.1 (ASTM D7253-16, bromothymol blue)</p> <p>Dynamic viscosity at 25°C, mPas ..... 3000 - 5500 (ASTM D4878-15, met. A)</p> <p>Solid content, % (m/m)* ..... 39 – 41 (MB-0107)</p> <p>* - parameter determined on customer's request</p>

<b>GENERAL DATA**</b>	<p>Density at temp. 25°C, g/ml .....~1.04</p> <p>Flash point, °C ..... above 200</p> <p><u>Contains BHT free antioxidants</u></p>
-----------------------	---

\*\*This information data does not constitute technical requirements and cannot be the basis for complaints.

<b>APPLICATION</b>	For production of flexible polyurethane slabstock foams exhibiting increased load bearing characteristics.
--------------------	--