

ROKOPOL FS3610

CHEMICAL NAME Dispersion of styrene acrylonitrile copolymer in oxyalkylated triol

TECHNICAL REQUIREMENTS

Appearance at 25°C White, opaque liquid

Hydroxyl value, mg KOH/g 40 – 45
(ASTM D4274-16, met. D)

Water content, % (m/m) max. 0.08
(ASTM D4672-12)

Acid value, mg KOH/g max. 0.1
(ASTM D7253-16, bromothymol blue)

Dynamic viscosity at 25°C, mPas 650 – 900
(ASTM D4878-15, met. A)

Solid content, % (m/m)* ~ 10
(MB-0107)

* - parameter determined on customer's request

GENERAL DATA**

Density at temp. 25°C, g/ml ~1.025

Flash point, °C above 200

Contains BHT free antioxidants

**This information data does not constitute technical requirements and cannot be the basis for complaints.

APPLICATION For production of flexible polyurethane slabstock foams exhibiting increased load bearing characteristics.