

ROKESTER 2421

CHEMICAL NAME	Polyester polyol
TECHNICAL REQUIREMENTS	Appearance at 25°C homogenous, straw to yellow liquid (visually) Hydroxyl value, mg KOH/g 240 – 255 (PN-EN ISO 2554:2001) Acid value, mg KOH/g 1.50 – 2.30 (PN-EN ISO 2114:2005, solvent: acetone) Water, % (m/m) max. 0.15 (PN ISO 760:2001) Dynamic viscosity at 25°C, mPas 3500 – 4000 (PN-EN ISO 3219:2000)
INFORMATIVE DATA*	Density at 25°C, g/ml ~1.23
	* These informative data are not technical requirements and cannot form the basis for any claims.
APPLICATION	Aromatic polyester polyol designed for the application in PUR/PIR foams.